RAKU® TOOL



EL-2200 / EH-2950-1

Epoxy Laminating and Multipurpose Resin

Temperature resistant up to 80°C, unfilled

© RAMPF Advanced Polymers GmbH & Co. KG

MAEI - Rev.Status: 03-2025/07/11 - GB

Page 1 / 2

Key Properties

- · Long pot life
- Good wetting properties
- Room temperature curing
- Temperature resistant up to 80°C

Applications

- Universal production of tools and tooling aids
- Production of substructures for Close Contour Pastes (EPS compatible)

Processing Properties

		Unit	EL-2200	EH-2950-1
Color	visual		colorless	yellowish
Mix ratio		pbw	100	16
Density	DIN 2811-1	g/cm³	ca. 1.10	ca. 1.01
Viscosity at 25 °C	DIN 53019-1	mPa·s	1,500 - 2,500	200 - 400

		Unit	EL-2200 / EH-2950-1
Mix viscosity at 25 °C	DIN 53019-1	mPa·s	1,000 - 1,200
Pot life at 25 °C	500 ml	min	50 - 60
Max. layer thickness		mm	8
Demold time		h	24

Cured / Mechanical Properties

Cure		Unit	EL-2200 / EH-2950-1 16h at RT + 14h at 100°C
Color		visual	yellowish
Density	ISO 1183	g/cm³	ca. 1.10
Deflection temperature, HDT	ISO 75	°C	75 - 80
Glass transition temperature, Tg	DSC	°C	75 - 80
Flexural strength	ISO 178	MPa	100 - 110
Flexural modulus	ISO 178	MPa	2,500 - 3,000

RAKU® TOOL

EL-2200 / EH-2950-1

Epoxy Laminating and Multipurpose Resin

Temperature resistant up to 80°C, unfilled



© RAMPF Advanced Polymers GmbH & Co. KG

MAEI - Rev.Status: 03 - 2025/07/11 - GB

Page 2 / 2

Processing

The processing temperature and material temperature should be between 20-25°C.

Degassing is recommended.

Impregnate each layer of cloths to construct the laminate layer by layer.

The mechanical properties and temperature resistance are only obtained through a post cure according to the recommended cure schedule.

Recommended cure schedule

After initial curing at room temperature for 12-24 hours depending on the size and thickness of the parts, the parts must be heated up to 100°C in steps and post cured for 14 hours at 100°C, then cooled down gradually. The curing time at room temperature, heating and cooling rate depend on the size and thickness of the parts.

Packaging	
RAKU® TOOL EL-2200	25 kg
RAKU® TOOL EH-2950-1	25 kg, 2 kg, 6 x 1 kg

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label. Partly used containers should always be sealed appropriately and used up as soon as possible.

Handling precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

RAMPF Advanced Polymers GmbH & Co. KG Robert-Bosch-Str.8 - 10 | D-72661Grafenberg T+49 7123 93 42-0

E advanced.polymers@rampf-group.com www.rampf-group.com

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby. The technical data sheet is not a specification, but contains only approximate values.