

## CP-6083 R / CP-6084 H

### Close Contour Paste

Machine applied epoxy paste

#### Key Properties

- Good edge strength
- Easy to machine, minimal dust
- Low exothermic
- Layer thickness 25 mm without slump on vertical surfaces

#### Applications

- Large-scale models
- Wind turbine blade models
- Boat models

#### Processing Properties

		Unit	CP-6083-R	CP-6084-H
Color	visual		gray	white
Mix ratio		pbw	100	100
Mix ratio		pbv	100	100
Density	ISO 1183	g/cm <sup>3</sup>	ca. 0.80	ca. 0.80

		Unit	CP-6083-R / CP-6084-H
Pot life at 25 °C	1000 ml	min	60 - 70
Max. layer thickness		mm	25
Machinable		h	14

#### Cured / Mechanical Properties

Cure		Unit	CP-6083-R / CP-6084-H 7 days at RT or 14h at 40°C	CP-6083-R / CP-6084-H 16h at RT + 14h at 80°C
Color		visual	gray	gray
Density	ISO 1183	g/cm <sup>3</sup>	ca. 0.85	ca. 0.85
Hardness	ISO 868	Shore D	65 - 70	68 - 72
Coefficient of thermal expansion	ISO 11359	10 <sup>-6</sup> K <sup>-1</sup>	65 - 75	57 - 67
Deflection temperature, HDT	ISO 75	°C	55 - 60	85 - 90
Glass transition temperature, Tg	DSC	°C	55 - 60	85 - 90
Compressive strength	ISO 604	MPa	40 - 45	48 - 52
Compressive modulus	ISO 604	MPa	1,500 - 2,000	1,800 - 2,300
Flexural strength	ISO 178	MPa	30 - 35	35 - 40
Flexural modulus	ISO 178	MPa	1,700 - 2,200	1,700 - 2,200
Linear shrinkage*		mm/m	ca. 1.00	ca. 1.00

\*measured on maximum layer thickness as stated above



**CP-6083 R / CP-6084 H**

**Close Contour Paste**

Machine applied epoxy paste

**Processing**

The processing temperature and material temperature should be between 20-25°C, never below 18°C.

Set up parameters for the dispensing machine are available on request. Check the mixing ratio before you start with the application. Please ensure the constant supply of compressed air. The longer the hose the higher the material pressure.

Avoid applying over 25 mm at once, for thicker layers it is recommended to apply the 2nd layer after the first one has gelled.

**Packaging**

RAKU® TOOL CP-6083-R	150 kg, 38 kg
RAKU® TOOL CP-6084-H	150 kg, 38 kg

**Storage**

Original containers should be kept tightly sealed and stored at ambient temperatures (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label. Partly used containers should always be sealed appropriately and used up as soon as possible.

**Handling precautions**

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.