

EP-2303, EP-2304 / EH-2936-2

Repair paste for boards

Fast cure at RT

Key Properties

- Sufficient pot life whilst fast curing
- Room temperature curing

Applications

- Repair of board materials

Processing Properties

| | | Unit | EP-2303 | EP-2304 | EH-2936-2 |
|-----------|----------|-------------------|----------|----------|-----------|
| Color | visual | | blue | green | white |
| Mix ratio | - | pbw | 100 | - | 50 |
| Mix ratio | - | pbw | - | 100 | 50 |
| Density | ISO 1183 | g/cm ³ | ca. 0.88 | ca. 0.88 | ca. 0.83 |

| | | Unit | EP-2303 / EH-2936-2 | EP-2304 / EH-2936-2 |
|-------------------|--------|--------|---------------------|---------------------|
| Color | | visual | blue | light green |
| Pot life at 25 °C | 100 ml | min | 15 - 20 | 15 - 20 |
| Machinable | | min | 90 - 120 | 90 - 120 |

Processing

The processing temperature and material temperature should be between 20-25°C. Mix the two components thoroughly in the ratio indicated and apply by spatula.

Packaging

| | |
|----------------------|---------|
| RAKU® TOOL EP-2303 | 5 kg |
| RAKU® TOOL EP-2304 | 5 kg |
| RAKU® TOOL EH-2936-2 | 0,50 kg |

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label. Partly used containers should always be sealed appropriately and used up as soon as possible.