RAKU-TOOL® CC-6013 & CB-6013



Close Contour Casting & Close Contour Block

Cast Polyurethane, density <1.0 g/cm³

© RAMPF Tooling Solutions GmbH & Co. KG

PC - Rev.-Status: 01- 2016/01/15

Page 1 of 2

Key Properties

- · Fine surface structure
- Very easily machined
- Similar quality to RAKU-TOOL[®] Modeling Boards without bonding lines

Applications

- Master models
- · Cubing models
- · Data control models

Advantages of Close Contour Casting & Close Contour Block

- Close Contour Casting (CC-6013) is supplied as a three dimensional shape which is already a close contour of your final shape
- Close Contour Block (CB-6013) is supplied as a customized size of a rectangular, unmachined block
- Quicker machining, less tool wear and less wastage through close contour shape
- Less manual finishing required as the surface is seamless, smooth and very dense
- No handling of liquid chemistry, concentration on milling technology
- Good dimensional stability as the material exhibits little stresses and is isotropic like board material
- High quality standard

Mechanical Properties

			CC-6013 & CB-6013
Color	visual		Brown
Density	ISO 1183	g/cm ³	ca. 0.80
Shore hardness D	max. value		70
Coefficient of thermal expansion	ISO 11359	10 ⁻⁶ K ⁻¹	65 – 70
Deflection temperature, HDT	ISO 75	°C	75 – 80
Compressive strength	ISO 604	MPa	38 – 43
Compressive modulus	ISO 604	MPa	1500 – 1800

Processing

The product should have a temperature of 20°C – 25°C during processing.

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

RAKU-TOOL® CC-6013 & CB-6013

Close Contour Casting & Close Contour Block

Cast Polyurethane, density <1.0 g/cm³



© RAMPF Tooling Solutions GmbH & Co. KG

PC - Rev.-Status: 01- 2016/01/15

Page 2 of 2

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

RAMPF Tooling Solutions GmbH & Co. KG Robert-Bosch-Str. 8-10 | D-72661 Grafenberg T +49.71 23. 93 42-1600 F +49.71 23. 93 42-1666 E tooling.solutions@rampf-gruppe.de

www.rampf-gruppe.de

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby