

## Water Clear 80D

Water-clear, semi-rigid polyurethane formulated

### Key Properties

- Excellent physical properties after RT cure
- Free of mercury, MOCA or TDI
- Excellent optical clarity as well as U.V. stability

### Applications

- For room temperature hand-batch or vacuum assisted casting methods

### Processing Properties

			Resin (Isocyanate)	Hardener (Polyol)
Mix ratio		pbw	100	50
		pbv	100	55
Density	ASTM D-792	g/cm <sup>3</sup>	ca. 1.16	ca. 1.05
Viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 900	ca. 4,000

			Mixture
Mix viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 1,200
Gel time at 77°F (25°C)		min	15-20
Demold time at 77°F (25°C)		h	2-4

### Cured / Mechanical Properties (approximate values)

Cure 1: 24 hours at 77°F Cure 2: 7 days at 77°F			Cure 1	Cure 2
Aspect	visual		Water Clear	Water Clear
Density	ASTM D-792	g/cm <sup>3</sup>	1.10	1.10
Shore hardness D	ASTM D-2240		75-85	75-85
Deflection temperature, HDT (66psi)	ASTM D-648	°F (°C)	140 (60)	140 (60)
Tensile strength	ASTM D-638	psi	8,000	10,000
Elongation at break	ASTM D-638	%	2	2
Flexural strength	ASTM D-790	psi	9,000	13,500
Flexural modulus	ASTM D-790	psi	250,000	325,000
Notched Izod	ASTM D-256	ft.-lbf/in	.5	.6
Linear shrinkage	ASTM D-2566	in/in	.001-.004	.001-.004

## Water Clear 80D

Water-clear, semi-rigid polyurethane formulated

---

### Processing

**The processing and material temperature should be between 68-77°F (20-25°C).**

For best results, de-air the material prior to casting, then pressurize to 60 psi until cured. However, if pressure cannot be used, this material has been designed for vacuum degas only. OC-5272 can be easily buffed when cured.

**Agitate the hardener and resin before use to ensure that the formula is homogenous.**

---

---

### Packaging

OC-5272 Quart Kit	3 lbs.
OC-5272 1 Gal. Kit	12 lbs.
OC-5272 5 Gal. Kit	60 lbs.
OC-5272 Drum Kit	675 lbs.

---

---

### Storage

Original containers should be kept tightly sealed and stored at ambient temperatures 59-86°F (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

---

---

### Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

---