RAKU® TOOL WB-1258



Board Material

Polyurethane Board for Tools and Molds

© RAMPF Advanced Polymers GmbH & Co. KG

PC - Rev.-Status: 01- 2024/08/02

Page 1 of 2

Key Properties

- Very high abrasion resistance whilst good dimensional stability and accuracy
- Homogeneous surface
- · High impact strength, good edge strength
- Very easily machined
- · Excellent resistance to chemicals, no swelling

Applications

- Pattern plates
- Core boxes

Mechanical Properties

			WB-1258
Color	visual		Orange
Density	ASTM D-792	lb/ft ³	ca. 74.9
Shore hardness D	ASTM D-2240		80 – 85
Coefficient of thermal expansion	ASTM D-3386	in/in/°F x 10 ⁻⁶	39 – 42
Glass Transition Temperature, Tg	DSC	°F	158 – 167
Compressive strength	ASTM D-695	psi	13,100 – 14,500
Flexural strength	ASTM D-790	psi	14,500 – 16,000
Abrasion	Taber	mm³/100R	50 – 55

Processing

The product should have a temperature of 68-77°F during processing.

Packaging

RAKU® TOOL WB-1258

39.4x19.7x [1.2, 2, 3, 3.9] in

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

RAKU® TOOL WB-1258

Board Material

Polyurethane Board for Tools and Molds



© RAMPF Advanced Polymers GmbH & Co. KG

PC - Rev.-Status: 01- 2024/08/02

Page 2 of 2

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

For information on adhesives and repair pastes see the corresponding individual technical data sheets.

RAMPF Group, Inc. 49037 Wixom Tech Drive Wixom, MI 48393 T +1 248. 295.0223 F +1 248. 295.0224 E info.us@rampf-group.com Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.