

2-3 PCF Rigid

Rigid polyurethane foam

Key Properties

- Excellent physical properties after RT cure
- Free of mercury, MOCA or TDI

Applications

- For hand-batch or meter-mix processing
- Ideal for use in packaging

Processing Properties

			Resin (Isocyanate)	Hardener (Polyol)
Mix ratio		pbw	100	90
		pbv	100	100
Density	ASTM D-792	g/cm ³	ca. 1.22	ca. 1.10
Viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 50	ca. 750

			Mixture
Mix viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 250
Cream time at 77°F (25°C)		sec	15-25
Rise time at 77°F (25°C)		sec	50-70
Tack Free time at 77°F (25°C)		sec	65-85
Demold time at 77°F (25°C)		min	5-15

Cured Properties

Cure 1: 7 days at 77°F

			Cure 1
Aspect	visual		Light Tan
Density	ASTM D-792	g/cm ³	0.032-0.048
Density	ASTM D-792	lb/in ³	0.0012-0.0017
Density	ASTM D-792	lb/ft ³	2-3

2-3 PCF Rigid

Rigid polyurethane foam

Processing

The processing and material temperature should be between 68-77°F (20-25°C).

FM-7026 can be dispensed using drill mixing methods. Use a high speed drill with a paint mixer attached and mix for ten seconds before pouring directly into the mold. Do not hand mix only, as the material does not receive the required shear and will not form the proper cell structure. To obtain quicker cycle times, preheat the mold to 120°F. Also the use of wax to release the foam from the mold is recommended.

Agitate the hardener before use to ensure that the formula is homogeneous.

Packaging

FM-7026 Quart Kit	3.8 lbs.
FM-7026 1 Gal. Kit	15.2 lbs.
FM-7026 5 Gal. Kit	76 lbs.
FM-7026 Drum Kit	855 lbs.

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures 59-86°F (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.
