

70A Water Clear

Water clear, semi-flexible polyurethane elastomer

Key Properties

- Excellent physical properties after RT cure
- Free of mercury, MOCA or TDI
- Low viscosity and uses materials that have excellent U.V. resistant qualities

Applications

- For hand-batch or vacuum assisted processing

Processing Properties

			Resin (Isocyanate)	Hardener (Polyol)
Mix ratio		pbw	60	100
		pbv	59	100
Density	ASTM D-792	g/cm ³	ca. 1.07	ca. 1.09
Viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 200	ca. 800

			Mixture
Mix viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 700
Gel time at 77°F (25°C)		min	12-18
Demold time at 77°F (25°C)		h	4-8

Cured / Mechanical Properties (approximate values)

Cure 1: 24 hours at 77°F + 16 hours at 150°F Cure 2: 7 days at 77°F			Cure 1	Cure 2
Aspect	visual		Clear	Clear
Density	ASTM D-792	g/cm ³	1.07	1.07
Shore hardness A	ASTM D-2240		65-75	65-75
Tensile strength	ASTM D-638	psi	500	450
Elongation at Break	ASTM D-638	%	75	85
Tear strength	ASTM D-624	pli	45	35
Linear shrinkage	ASTM D-2566	in/in	0.001-0.005	0.001-0.005

70A Water Clear

Water clear, semi-flexible polyurethane elastomer

Processing

The processing and material temperature should be between 68-77°F (20-25°C).

Certain silicone rubbers, including platinum silicones, will inhibit the OC-5000 series. Tin based silicones will yield the most favorable results. It is recommended that a test plaque be cast on the outside of the silicone tool to test for compatibility. Contact your RAMPF Group Inc. representative for more information. For best results, de-air the material prior to casting, then pressurize to 60 psi until cured. If pigment has been added to the hardener component, it will separate during storage.

Agitate hardener before mixing to ensure that the formula is homogeneous.

Packaging

OC-5070 Quart Kit	3.2 lbs.
OC-5070 1 Gal. Kit	12.8 lbs.
OC-5070 5 Gal. Kit	64 lbs.
OC-5070 Drum Kit	720 lbs.

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures 59-86°F (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.
