

# Rapid Cast / Polypropylene / Flex / Black

Shore D polyurethane system

## Key Properties

- Excellent physical properties after RT cure
- Free of mercury, MOCA or TDI

## Applications

- Formulated for room temperature meter-mix dispensing systems and short mold cycle times

## Processing Properties

			Resin (Isocyanate)	Hardener (Polyol)
Mix ratio		pbw	100	88
		pbv	100	100
Density	ASTM D-792	g/cm <sup>3</sup>	ca. 1.26	ca. 1.10
Viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 100	ca. 1,200

			Mixture
Mix viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 500
Gel time at 77°F (25°C)		sec	60-80
Demold time at 77°F (25°C)		min	10-15

## Cured / Mechanical Properties (approximate values)

Cure 1: 24 hours at 77°F Cure 2: 7 days at 77°F			Cure 1	Cure 2
Aspect	visual		Black	Black
Density	ASTM D-792	g/cm <sup>3</sup>	1.14	1.14
Shore hardness D	ASTM D-2240		70-80	75-85
Deflection temperature, HDT (66psi)	ASTM D-648	°F (°C)	194 (90)	194 (90)
Tensile strength	ASTM D-638	psi	4,700	6,500
Elongation at Break	ASTM D-638	%	9	9
Flexural strength	ASTM D-790	psi	7,500	9,700
Flexural modulus	ASTM D-790	psi	185,000	210,000
Notched Izod	ASTM D-256	ft-lbf/in	1.1	1.1
Linear shrinkage	ASTM D-2566	in/in	0.001-0.005	0.001-0.005

**Rapid Cast / Polypropylene / Flex / Black**

Shore D polyurethane system

---

### Processing

**The processing and material temperature should be between 68-77°F (20-25°C).**

RC-0555 can be used at room temperature. Meter-mix equipment is recommended due to the short working life of the formulation. T

**Agitate the hardener and resin before use to ensure that the formula is homogeneous.**

---

---

### Packaging

RC-0555 Quart Kit	3.76 lbs.
RC-0555 1 Gal. Kit	15.04 lbs.
RC-0555 5 Gal. Kit	75.2 lbs.
RC-0555 Drum Kit	846 lbs.

---

---

### Storage

Original containers should be kept tightly sealed and stored at ambient temperatures 59-86°F (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

---

---

### Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

---