

50A / Excellent Green Strength / 10 Min. Gel / Black

50 shore A polyurethane elastomer

Key Properties

- Excellent physical properties after RT cure
- Free of mercury, MOCA or TDI
- Excellent green strength for quick demold times

Applications

- For hand-batch processing

Processing Properties

			Resin (Isocyanate)	Hardener (Polyol)
Mix ratio		pbw	40	100
		pbv	37	100
Density	ASTM D-792	g/cm ³	ca. 1.18	ca. 1.08
Viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 1,250	ca. 600

			Mixture
Mix viscosity at 77°F (25°C)	ASTM D-2393	cP	ca. 900
Gel time at 77°F (25°C)		min	8-12
Demold time at 77°F (25°C)		min	60-120

Cured / Mechanical Properties (approximate values)

			Cure 1	Cure 2
Cure 1: 24 hours at 77°F + 1 hour at 150°F				
Cure 2: 7 days at 77°F				
Aspect	visual		Black	Black
Density	ASTM D-792	g/cm ³	1.08	1.08
Shore hardness A	ASTM D-2240		45-55	45-55
Tensile strength	ASTM D-638	psi	350	370
Elongation at Break	ASTM D-638	%	160	150
Tear strength	ASTM D-624	pli	40	40
Linear shrinkage	ASTM D-2566	in/in	0.001-0.003	0.001-0.003

50A / Excellent Green Strength / 10 Min. Gel / Black

50 shore A polyurethane elastomer

Processing

The processing and material temperature should be between 68-77°F (20-25°C).

For best results, place the poured tool into a pressure vessel and pressurize to 60 psi until cured.

The hardener component does contain black pigment that will separate during storage.

Agitate Hardener and Resin before mixing to ensure a homogenous formulation.

Packaging

VA-1515 Quart Kit	2.8 lbs.
VA-1515 1 Gal. Kit	11.2 lbs.
VA-1515 5 Gal. Kit	56 lbs.
VA-1515 Drum Kit	630 lbs.

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures 59-86°F (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.
