

## Board Material

### Polyurethane Board for Styling & Design

#### Key Properties

- Very light weight with good surface
- Easily shaped
- Good heat resistance
- Resistant to organic solvents

#### Applications

- Design study
- CNC program checking
- Supporting structures for tooling pastes
- Negative mold for casting

#### Mechanical Properties

			SB-0130
Color	visual		Light yellow
Density	ASTM D-792	g/cm <sup>3</sup> (lb/ft <sup>3</sup> )	ca. 0.13 (ca. 8.0)
Coefficient of thermal expansion	ASTM D-2240	10 <sup>-6</sup> K <sup>-1</sup> (in/in/°F x 10 <sup>-6</sup> )	50 (28)
Deflection temperature, HDT	ASTM D-3386	°C (°F)	- (-)
Compressive strength	ASTM D-648	MPa (psi)	1.5-2.0 (218-290)
Flexural strength	ASTM D-695	MPa (psi)	2.4 (348)

#### Processing

The product should have a temperature of 20 – 25°C (68 - 77°F) during processing.

#### Packaging

RAKU® TOOL SB-0130	2 x 24 x 96
	4 x 24 x 96
	6 x 24 x 96
	8 x 24 x 96
	2 x 48 x 96
	4 x 48 x 96
	6 x 48 x 96
	8 x 48 x 96

#### Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

---

### **Handling Precautions**

---

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

---

**For information on adhesives and repair pastes see the corresponding individual technical data sheets.**